CALSTONE

Masonry Mortar Type S

- · Pre-blended color and uniformity
- Convenient handling & transporting
- · Consistent quality and yield
- · Excellent workability & board life
- · Strong and durable
- · Has a long lasting mortar bond
- Uniform aggregate sizes ensure easy mixing

Calstone Type S Masonry Mortar exceeds the requirements and standards or ASTM C270 and C387.

SIZE & YIELD

Our 80 lb (36.3 kg) bag will lay up to 40 standard bricks and 15 standard blocks.

COLORS

Calstone Type S Masonry Mortar is stocked and available in gray and tan. Custom colors available by special order.

PREPARATION

Remove all loose and/or deteriorated material as well as any surface contaminants such a soil, paint, grease, etc.

MIXING

Empty the contents of the bag into a clean wheelbarrow, mortar box, mechanical mixer or other mixing vessel. Form a crater with a shovel or hoe in the center of the dry mix. Mix sufficient water to achieve desired workability. For hand mixing—Blend dry mix with a shovel or hoe from the outer edges working the material towards the center. Continue mixing until all free water is used and all the aggregate is uniformly coated with cement. For mechanical mixing—Mix the material for three minutes.

FINISHING

Joints can be finished when material has begun to set and the surface has a thumbprint hard consistency. Mortar joints can be finished with a jointing tool.

CURING

Protect from direct sunlight, wind, rain and frost during the curing period.

HEALTH AND SAFETY

- Product is alkaline.
- Do not ingest.
- Avoid breathing dust.
- May cause irritation to skin and eyes.
- Refer to Material Safety Data Sheet (MSDS) for additional information.
- Keep out of reach of children.

